

# AX-FJ

#### 1. Introduction:

Product for the equalization of nubuck leathers.

### 2. Description:

Product for the equalization of nubuck leathers.

### 3. Composition:

Solids:	4.0% ± 1
pH:	8.5 ± 1
Viscosity at 25°C:	<50 cP

#### 4. Properties:

Leveling and fixing for all types of suede and nubuck, helping to match colors but maintaining the writing effect and providing a very good waxy touch on suede, nubuck and split leather.

## 5. Minimum storage capability:

The product may be stored with its container tightly closed in a well-ventilated place at a temperature ranging from +5°C to +35°C. Sealed containers have a service life of 6 months.

## 6. Application:

It can be applied by spray either to match the colors of suedes while preserving the writing effect or to increase the fastness to the rubbing of the powder. Apply 1: 1 with water to set the powder of the suede. Add up to 50 grams of pigment or colorant to either match or enhance colors. To have a better rubbing fastness, add between 0.5% and 0.8% of our crosslinking agent AX-EAN.

#### 7 Safety

When handling this product the instructions set out in the safety data leaflet must be observed. The relevant safety and precautionary measures for hygiene in the workplace must also be followed when working with chemical products.

## 8. Observations:

The instructions given in this publication are based on the current stand of our knowledge and experience. This does not presuppose any judicial guarantee concerning certain properties nor their suitability for any application in particular. Given the many influences that may occur during the handling and use of our products, the persons handling or transforming them are not exempt from carrying out their own controls or tests. All those receiving our products will be responsible for observing all existing patent rights as well as all current laws and regulations.

Update: 20.11.21

Finishing

More info