

Limeqin AES

1. Description:

Mixture of alkylol amines

2. Chemical nature:

Preparation based on an aliphatic ammonium compound and nonionic surfactant.

3. Characteristical features:

Appearance:	Oily liquid.
Colour:	Colorless and transparent.
Active substance:	40%±1%
pH (1:10):	8.0±1

4. Properties:

Preparation based on an aliphatic ammonium compound and nonionic surfactant.

5. Storage capacity:

The product may be stored with its container tightly closed in a well-ventilated place at a temperature ranging from +5°C to +35°C. Sealed containers have a service life of 6 months.

6. Application:

It helps to the uniform sulphur and lime penetration into the structure of the skin, notably reducing the duration of the process. It returns to the characteristics of an old unhair without fearing loss of skin substance. Softens the rapid swelling action of the unhairing components, a highly valued subject especially when working at low temperatures. Easily removes the roots and pigments of the skin, obtaining cleaner and less swollen skin, which significantly reduces wrinkles and neck veins. It can be mixed with water in any proportion. For the soaking of vegetable pre-tanning leathers, especially goats, sheep and bastards, it is advisable to pump the tanned ones for 30 min. at 60 min., with:

300%	Water 30-35°C
2.0-2.5%	Limeqin AES
1.0%	Sodium Sulfite

(Percentage on the dry weight of the skin)

Then rinse well. This procedure cleans and degreases and has given good results on leather that must undergo mineral retanning with chrome or aluminum tanning agents (Tanqin AS).

7. Safety:

When handling this product the instructions set out in the safety data leaflet must be observed. The relevant safety and precautionary measures for hygiene in the workplace must also be followed when working with chemical products.

8. Observations:

The instructions given in this publication are based on the current stand of our knowledge and experience. This does not presuppose any judicial guarantee concerning certain properties nor their suitability for any application in particular. Given the many influences that may occur during the handling and use of our products, the persons handling or transforming them are not exempt from carrying out their own controls or tests. All those receiving our products will be responsible for observing all existing patent rights as well as all current laws and regulations.

Update: 26.05.22

Beamhouse
and Wet

Unhairing
and Liming
Auxiliaries

More info

quimicainternacional.com