

Limeqin AM

1. Description:

Auxiliary unhairing agent.

2. Chemical nature:

Amines in aqueous solution.

3. Characteristical features:

Appearance:	Liquid.
Solid content:	68.5±2
pH value (1:10):	11.0±1
Colour:	Yellowish.

4. Properties:

Miscible in water in any proportion. Facilitates uniform penetration of the unhairing chemicals throughout the skin; being able to shorten the duration of the process. Slows down and softens the swelling effect produced by sulfur and/or caustic soda. Given the advantage of using Limeqin AM, even at low temperatures and even at room temperature, the result is a cleaner and more open grain, with fewer wrinkles.

5. Storage capacity:

The product may be stored with its container tightly closed in a well-ventilated place at a temperature ranging from +5°C to +35°C. Sealed containers have a service life of 6 months.

6. Application:

For the effect to be favorable, the product must be added together with the last addition of unhairing products. In the case of unhairing with hair recovery, the product must be added at the beginning of unhairing and between 30 and 40 minutes before adding the lime that is going to immunize the hair or together with it. The amounts to be added range between 0.5 and 1.0%

7. Safety:

When handling this product the instructions set out in the safety data leaflet must be observed. The relevant safety and precautionary measures for hygiene in the workplace must also be followed when working with chemical products.

8. Observations:

The instructions given in this publication are based on the current stand of our knowledge and experience. This does not presuppose any judicial guarantee concerning certain properties nor their suitability for any application in particular. Given the many influences that may occur during the handling and use of our products, the persons handling or transforming them are not exempt from carrying out their own controls or tests. All those receiving our products will be responsible for observing all existing patent rights as well as all current laws and regulations.

Update: 26.05.22

Beamhouse
and Wet

Unhairing
and Liming
Auxiliaries

More info

quimicainternacional.com