

Helpa MB

1. Introduction:

Auxiliary product for leather retanning.

2. Description:

Combination of aromatic sulfonic acids and other special penetrating additives.

3. Composition:

Appearance:	Powdery solid.
Character:	Anionic.
Active matter:	=80%
PH value (1:10):	7.5 ± 0.7
Color:	Beige.
VOC:	0%

4. Properties:

Helpa MB improves the penetration capacity of retanning and coloring products, allowing both these and those to do so in a homogeneous way and achieving greater equalization and distribution of the products through the use of these products. Helpa MB is easily soluble in water. It also accelerates the penetration of vegetable tanning products and other anionic products, reducing astringency when go through the leather. Due to the neutralization produced when pass into the leather, before the retanning of chrome-tanned leathers, a relaxed and homogeneous penetration of the retanning agents and dyes added later is produced. The result is a crust with a more even and intense dying and where the neck veins are less noticeable than with a conventional dispersant. The product does not reduce the dying intensity considerably.

5. Minimum storage capability:

The product may be stored with its container tightly closed in a well- ventilated place at a temperature ranging from +5°C to +35°C. Sealed containers have a service life of 6 months.

6. Application:

The use of Helpa MB results a quite acceptable pore fineness since it does not overload the grain, rather, the discharge given the low reactivity it causes in it. The flower remains elastic even when using highly astringent retanning agents. In a conventional retanning, about 3% Helpa MB is used, 15'/20' minutes before the addition of the main retanning process.

7. Safety:

When handling this product the instructions set out in the safety data leaflet must be observed. The relevant safety and precautionary measures for hygiene in the workplace must also be followed when working with chemical products.

8. Observations:

The instructions given in this publication are based on the current stand of our knowledge and experience. This does not presuppose any judicial guarantee concerning certain properties nor their suitability for any application in particular. Given the many influences that may occur during the handling and use of our products, the persons handling or transforming them are not exempt from carrying out their own controls or tests. All those receiving our products will be responsible for observing all existing patent rights as well as all current laws and regulations.

Update: 01.06.22

Beamhouse
and Wet

Retanning
Auxiliaries

More info

quimicainternacional.com