

1. Description:

Auxiliary product for leather industry.

2. Presentation:

Stabilizing agent for cationic fatliquoring agents with an additional fatliquoring effect.

3. Composition:

Ethoxylated fatty amine derivative.

Appearance:	Liquid
Nature:	Cationic
Solids content:	37
PH Value (1:10):	7,0±1

4. Properties:

Not only it makes stable the cationic fatliquoring of the leathers, but it also has an additional softening effect. It is also used as an auxiliary dyeing agent as a charge changer for the anionic dyeing agents, giving full and shiny dyeings. It is also appropriate for the wetting-back of leathers for glove-making.

5. Minimum storage capacity:

The product can be stored in its well closed container, in a well ventilated place, at temperatures between +5° and +35°C. In its sealed container it lasts 12 months.

6. Application:

Added after the dyeing process it helps to fix the colour and to obtain intenser colours. It also presents an effect smoothly damping.

7. Safety:

When handling this product the instructions set out in the safety data leaflet must be observed. The relevant safety and precautionary measures for hygiene in the workplace must also be followed when working with chemical products.

8. Observations:

The instructions given in this publication are based on the current stand of our knowledge and experience. This does not presuppose any judicial guarantee concerning certain properties nor their suitability for any application in particular. Given the many influences that may occur during the handling and use of our products, the persons handling or transforming them are not exempt from carrying out their own controls or tests. All those receiving our products will be responsible for observing all existing patent rights as well as all current laws and regulations.

Update: 20.09.14

Beamhouse
and Wet

Dyeing
Auxiliaries