

Helpa TR

1. Introduction:

Auxiliary for the leather industry.

2. Presentation:

The Helpa TR is a special product of ethoxylation.

3. Chemical-physical characteristics:

Ethoxylated Oleilamine specially modified.

Appearance:	Liquid.
Color:	Light brown.
Character:	Non ionic.
Water content:	40% approx.
PH(1:10):	8.0 +/-1.

4. Properties:

The Helpa TR improves the penetration of anionic dyes to give a leather dyed with a uniform penetration. The product solidifies between 0°C and 5°C without loss of quality.

5. Storage capacity:

The product may be stored with its container tightly closed in a well-ventilated place at a temperature ranging from +5°C to +35°C. Sealed containers have a service life of 12 months.

6. Usage:

The Helpa TR is suitable for get a penetrated dyeing without lowering the intensity. It should be applied after retanning in a new float. After the re-tanning, wash leathers, new float (50% water) adding 0.8 to 1.5% of the Helpa TR, run 10 min., add the dye, run 30 min., crossing control, continue adding water at 60°C. Then continue with the conventional fatliquoring.

7. Safety:

When handling this product the instructions set out in the safety data leaflet must be observed. The relevant safety and precautionary measures for hygiene in the workplace must also be followed when working with chemical products.

8. Observations:

The instructions given in this publication are based on the current stand of our knowledge and experience. This does not presuppose any judicial guarantee concerning certain properties nor their suitability for any application in particular. Given the many influences that may occur during the handling and use of our products, the persons handling or transforming them are not exempt from carrying out their own controls or tests. All those receiving our products will be responsible for observing all existing patent rights as well as all current laws and regulations.

Update: 16.04.17

Beamhouse
and Wet

Dyeing
Auxiliaries