

Extracto de Mimosa GS

1. Introducction:

Auxiliary product for the leather industry.

2. Presentation:

Vegetable tanning agent.

3. Composition:

| Appearance: | Brown powder, hygroscopic. |
|-----------------|----------------------------|
| Nature: | Anionic. |
| PCP. | Non. |
| Tannins: | 70+-2% |
| PH Value (1:5): | 4,2 - 4,8 |

4. Properties:

The Mimosa extract is water-soluble in cold and warm water and has the faollowing features: fast penetration, excellent capacity, very clear leathers, good fixation power and pleasant cream tone.

For the retanning of chrome leathers, using Mimosa extract allows to fill up flanks and bellies, to benefit the scouring, maintain the embossing of the ironing, giving an excellent burning effect.

5. Minimum storage capacity:

The product can be stored in its well closed container, in a well ventilated place, at temperatures between +5 and +35°C. In its sealed container, it lasts 12 months.

6. Application:

It can be applied solely or combined with other vegetable extracts, synthetics and/or auxiliaries. The advised quantities are the following, over pelt weight: 25 to 30% of Mimosa extract for side leather vegetable tannings, from 40 to 45% for sole leather tannings; over shaved weight: from 5 to 15% of Mimosa extract for retanning of chrome leathers.

7 Safety

When handling this product the instructions set out in the safety data leaflet must be observed. The relevant safety and precautionary measures for hygiene in the workplace must also be followed when working with chemical products.

8. Observations:

The instructions given in this publication are based on the current stand of our knowledge and experience. This does not presuppose any judicial guarantee concerning certain properties nor their suitability for any application in particular. Given the many influences that may occur during the handling and use of our products, the persons handling or transforming them are not exempt from carrying out their own controls or tests. All those receiving our products will be responsible for observing all existing patent rights as well as all current laws and regulations.

Update: 28.03.17 Beamhouse and Wet

Tanning Agents

More info