

# Tanqin GLT 50

## 1. Introduction:

Pretanning and retanning agent.

## 2. Description:

Glutaraldehyde in aqueous solution.

## 3. Composition:

Appearance:	Liquid.
Active matter:	50% approx.
pH value (1:10):	3.5-4.0
Colour:	Light yellowish.

## 4. Properties:

Resistant to electrolytes and compatible with pickle acids, neutral salts and mineral tanning agents. It gives the leathers a round, extremely soft touch and good tinctorial capacity, even for intense colours. Good fastness to washing and resistance to perspiration. It is not advisable for white items due to the yellowing it causes on the skin.

## 5. Minimum storage capability:

The product may be stored with its container tightly closed in a well-ventilated place at a temperature ranging from +5°C to +35°C. Sealed containers have a service life of 6 months.

## 6. Application:

The field of application of this product is very wide, so talking about quantities and/or positions in a given process becomes very complicated. The product is recommended for a wide variety of items; As a tanning agent for wet white articles, chrome tanning, retanning of chrome-tanned leather, tanning and pre-tanning of vegetable-tanned leather... It is recommended to dilute the product 1:2 to 1:5 in water before adding it. Indicative quantities range from 0.5% to 4.0%, taking into account that, at pH's below 4.0, the product will penetrate, providing grain finesse and as we raise the pH, the product and the skin increase their affinity, helping even to improve the exhaustion of other products.

## 7. Safety:

When handling this product the instructions set out in the safety data leaflet must be observed. The relevant safety and precautionary measures for hygiene in the workplace must also be followed when working with chemical products.

## 8. Observations:

The instructions given in this publication are based on the current stand of our knowledge and experience. This does not presuppose any judicial guarantee concerning certain properties nor their suitability for any application in particular. Given the many influences that may occur during the handling and use of our products, the persons handling or transforming them are not exempt from carrying out their own controls or tests. All those receiving our products will be responsible for observing all existing patent rights as well as all current laws and regulations.

Update: 23.02.23

Beamhouse  
and Wet

Tanning  
Agents

More info

[quimicainternacional.com](http://quimicainternacional.com)