

# Qinoil BSF

#### 1. Introduction:

Sulfochlorinated paraffin-based compound.

# 2. Description:

Sulfochlorinated paraffin-based compound.

3. Composition:

Appearance:	Liquid.
Colour:	Beige.
Active matter:	65%±3%
Character:	Anionic.
pH (10%):	6.5-7.5
lodine value:	25
Total SO3:	3.10 approx.
Electrolyte resistance:	Good

# 4. Properties:

Greasing agent that presents a good fixation and prevents looseness of the grain. It gives the leather good firmness and, given its power of adhesion to the leather fibers, increases tear strength.

## 5. Minimum storage capability:

The product may be stored with its container tightly closed in a well- ventilated place at a temperature ranging from +5°C to +35°C. Sealed containers have a service life of 6 months.

### 6. Application:

Its use is recommended for all types of leather: goats, wool, bovine,... As well as for split leather of all kinds. It is specifically recommended for the production of patent leather. Applicable to leather directed to pastel or white tones without risk of yellowing. Stable to vegetable baths, salts, acids and hard water. Its use in combi-licker greasings, that is, with greasing agents of various types, increases their fixation.

#### 7. Safety:

When handling this product the instructions set out in the safety data leaflet must be observed. The relevant safety and precautionary measures for hygiene in the workplace must also be followed when working with chemical products.

# 8. Observations:

The instructions given in this publication are based on the current stand of our knowledge and experience. This does not presuppose any judicial guarantee concerning certain properties nor their suitability for any application in particular. Given the many influences that may occur during the handling and use of our products, the persons handling or transforming them are not exempt from carrying out their own controls or tests. All those receiving our products will be responsible for observing all existing patent rights as well as all current laws and regulations.

Update: 25.01.23

Beamhouse and Wet

More info