Qinoil MX01

1. Presentation:
Product for the fatliquori ngof leather.

2. Composition:
Based onsulphate and sulphite oilswith special additives.

Appearance:	Oilish liquid
Nature:	Anionic
Solidscontent:	52+-2
PH Value (1:1O):	6.5-7.5
Colour:	Reddish brown
VOC:	0.53%

3. Properties:
This composition gives a fine emulsion when mixed with water. It is not stable to mineral agents baths and to high salt concentrations. Gives to the leather a soft touch, grain firmness and a good fullness because of the good penetration that does not overcharge the grain. It is distributed evenly inside of the leather. It provides good properties far scouring over split leather and also a noticeable writing effect anda shiny plush.

4. Minimum storage capacity:
The product can be stored in its well closed container, in a well ventilated place at temperatures between +5 and +35ºC. 1n its sealed container it lasts 6months.

5. Application:
This fatliquoring agent has been designed to be used only in the main fatliquoring process in quantities around 7%. To be part of a combi-licker the application will be between 2 and 5%, according to the needs of the final item.

7. Safety:
When handling this product the instructions set out in the safety data leaflet must be observed. The relevant safety and precautionary measures for hygiene in the workplace must also be followed when working with chemical products.

8. Observations:
The instructions given in this publication are based on the current stand of our knowledge and experience. This does not presuppose any judicial guarantee concerning certain properties nor their suitability for any application in particular. Given the many influences that may occur during the handling and use of our products, the persons handling or transforming them are not exempt from carrying out their own controls or tests. All those receiving our products will be responsible for observing all existing patent rights as well as all current laws and regulations.

Update: 08.10.15

Beamhouse and Wet

Fatliquoring