

# Qinoil S2C

#### 1. Introduction:

Product for the leather fatliquoring process.

# 2. Description:

Fish oxidized sulphited oil.

### 3. Composition:

Appearance:	Liquid.
Character:	Anionic.
Active substance:	85%±1%
pH value (1:10):	7.0±1.0
Color:	Brown.

# 4. Properties:

For all types of leather that must be soft. The Qinoil S2C also provides a round and full touch. Given its composition, this fatliquor can be used as a single fatliquor or as part of a "combi-licker" grease pack.

### 5. Minimum storage capability:

The product may be stored with its container tightly closed in a well- ventilated place at a temperature ranging from +5°C to +35°C. Sealed containers have a service life of 6 months.

## 6. Application:

It can be applied during the rechroming, neutralization, retanning and main fatliquoring processes. The quantities to be applied will depend both on the final softness of the article to be achieved and on the place where the fatliquor is placed. Normally, between 0.5% and 1.0% is used when rechroming thick leathers, while in the main fatliquoring from 2.0% to 4.0%.

#### 7. Safety:

When handling this product the instructions set out in the safety data leaflet must be observed. The relevant safety and precautionary measures for hygiene in the workplace must also be followed when working with chemical products.

# 8. Observations:

The instructions given in this publication are based on the current stand of our knowledge and experience. This does not presuppose any judicial guarantee concerning certain properties nor their suitability for any application in particular. Given the many influences that may occur during the handling and use of our products, the persons handling or transforming them are not exempt from carrying out their own controls or tests. All those receiving our products will be responsible for observing all existing patent rights as well as all current laws and regulations.

Update: 01.07.22

Beamhouse and Wet

More info