

1. Description:

Product for leather's retanning.

2. Presentation:

Polymer retanning agent.

3. Composition:

Acrylic polymer water solution.

Appearance:	Liquid.
Nature:	Anionic.
Solids content:	35% approx.
PH value (1:10):	4,0±1
Colour:	Yellowish.

4. Properties:

It provides the leather with grain firmness and an average fullness, by leaving it more reinforced than if processed by a normal acrylic. It is stable to acids and can be used after the re-chroming of some items and before neutralising. It can be used together with other anionic products in normal working quantities. It improves the exhaustion of the chrome salts used at any procedure where this product was present.

5. Minimum storage capacity:

The product can be stored in its well closed container, in a well ventilated place at temperatures between +5° and +35°C. In its sealed container it lasts 12 months.

6. Application:

We recommend its use for milled items as it allows a very homogeneous dissipation due to its reduced molecular size. This gives a fine and uniform grain. It also is used to be applied over wet white items where, given their own features, it intensifies aldehydic tanning agents' tanning effect.

7. Safety:

When handling this product the instructions set out in the safety data leaflet must be observed. The relevant safety and precautionary measures for hygiene in the workplace must also be followed when working with chemical products.

8. Observations:

The instructions given in this publication are based on the current stand of our knowledge and experience. This does not presuppose any judicial guarantee concerning certain properties nor their suitability for any application in particular. Given the many influences that may occur during the handling and use of our products, the persons handling or transforming them are not exempt from carrying out their own controls or tests. All those receiving our products will be responsible for observing all existing patent rights as well as all current laws and regulations.

Update: 12.09.14

Beamhouse
and Wet

Polimeric
retanning agents