

Tanqin SM8

1. Introduction:

Maleic styrene resin.

2. Description:

Styrene maleic copolymer.

3. Composition:

Appearance:	Liquid.
Character:	Anionic.
Solid content:	25% approx.
pH value (1:10):	8.5±1
Color:	Yellowish.
VOC:	0%

4. Properties:

Gives grain firmness to empty and loose skin. It can be used for soft articles with a rubbery final appearance. It can also be indicated for milled articles.

5. Minimum storage capability:

The product may be stored with its container tightly closed in a well-ventilated place at a temperature ranging from +5°C to +35°C. Sealed containers have a service life of 6 months.

6. Application:

Its highest degree of effectiveness is obtained when it is applied before rechroming the skin. Used in neutralizing or at the beginning of retanning, it gives the leather a high degree of softness and a firm and smooth grain.

7. Safety:

When handling this product the instructions set out in the safety data leaflet must be observed. The relevant safety and precautionary measures for hygiene in the workplace must also be followed when working with chemical products.

8. Observations:

The instructions given in this publication are based on the current stand of our knowledge and experience. This does not presuppose any judicial guarantee concerning certain properties nor their suitability for any application in particular. Given the many influences that may occur during the handling and use of our products, the persons handling or transforming them are not exempt from carrying out their own controls or tests. All those receiving our products will be responsible for observing all existing patent rights as well as all current laws and regulations.

Update: 25.01.23

Beamhouse
and Wet

Polimeric
retanning agents

More info

quimicainternacional.com