

# Tanqin A24

## 1. Introduction:

Product for leather retanning.

## 2. Description:

Formulation of retanning products containing dicyandiamide.

## 3. Composition:

Appearance:	Powder.
Nature:	Anionic.
Solids content:	> 85%.
pH value (1:10):	5,0±1
Colour:	Beige.

## 4. Properties:

Purposed for full as well as for corrected grain items. It provides grain firmness to leather while keeping the pore fine and good buffability. The fact that some of the tanning action products are condensed explains Tanqin A24 affinity to chrome leathers and its even dispersion all over and among the inter-fiber spaces. As the added resin is neither hard nor cracky, but elastic and tough, it provides leather with a pleasant fullness and touch, without altering chrome leather's nature.

## 5. Minimum storage capacity:

The product can be stored in its well closed container, in a well ventilated place at a temperature between +5 and +35°C. In its sealed container it lasts 12 months.

## 6. Application:

Compatible with natural and synthetic tanning agents, fatliquoring agents, colouring agents and anionic auxiliary products. It can be added as a powder straight to the drum, once leather has been neutralised, to the same bath or apart to a new one.

Occasionally, any natural, synthetic or chrome tanning agent can be added, in order to improve even more the fullness or touch.

## 7. Safety:

When handling this product the instructions set out in the safety data leaflet must be observed. The relevant safety and precautionary measures for hygiene in the workplace must also be followed when working with chemical products.

## 8. Observations:

The instructions given in this publication are based on the current stand of our knowledge and experience. This does not presuppose any judicial guarantee concerning certain properties nor their suitability for any application in particular. Given the many influences that may occur during the handling and use of our products, the persons handling or transforming them are not exempt from carrying out their own controls or tests. All those receiving our products will be responsible for observing all existing patent rights as well as all current laws and regulations.

Update: 04.07.16

Beamhouse  
and Wet

Vegetal  
retanning agents