

# Tanqin VCT 20

## 1. Description:

Vegetal synthetic based retanning agent.

#### 2. Chemical nature:

Extracts derivatives and refilling agents.

#### 3. Characteristical features:

Appearence:	Powder
Colour:	Clear brown
PH:	2,5-3,1
Solids:	80-85
Charge:	Anionic

# 4. Properties:

Anionic and neutral organic compounds mix that provides a good filling effect. It is physically absorbed between the leather's fibers, acting more intensely over the less compact areas, as it equalizes the compacity all over the leather piece. Given its nature it is indicated for articles of low stretchiness. It provides dye's equal matching as well as a good touch and tube effect.

# 5. Storage capacity:

The product may be stored with its container tightly closed in a well-ventilated place at a temperature ranging from +2°C to +35°C. Sealed containers have a service life of 12 months.

### 6. Application:

Given its character, it can be applied during the retanning procedure, added to the fatliquoring agent it helps with its penetration. Depending on if it is applied as an only tanning agent or in combination with others, we recommend adding between 2% and 4% in the first case and between 6% and 8% in the second one.

#### 7. Safety:

When handling this product the instructions set out in the safety data leaflet must be observed. The relevant safety and precautionary measures for hygiene in the workplace must also be followed when working with chemical products.

# 8. Observations:

The instructions given in this publication are based on the current stand of our knowledge and experience. This does not presuppose any judicial guarantee concerning certain properties nor their suitability for any application in particular. Given the many influences that may occur during the handling and use of our products, the persons handling or transforming them are not exempt from carrying out their own controls or tests. All those receiving our products will be responsible for observing all existing patent rights as well as all current laws and regulations.

Update: 12.09.14
Beamhouse
and Wet

Vegetal retanning agents

More info