

1. Description:

Auxiliary product for leather finishing.

2. Presentation:

RU-1403 is an aliphatic polyurethane top.

3. Composition:

Polyurethane dispersion in an aqueous environment.

Appearance:	Transparent liquid.
Colour:	Yellowish.
Dry material:	30% approx.
Specific weight at 25°C:	0,976 g/cm ³
Viscosity:	100 cp 1/60 approx.
Flammability:	34°C
Film hardness:	Medium.
Glowing degree:	Shiny.
COV content:	69,85%

4. Properties:

RU-1403 offers a firm and flexible layer. It is especially suitable for fixations which require a high solidity against alcohol and dry or wet rubbing. Good light fastness and good resistance against UV rays.

5. Minimum storage capacity:

The product can be stored in its well closed container in a well ventilated place at temperatures between +5° and +35°C, both for transport and storage.

In its sealed container it lasts 12 months.

6. Application:

Once cross-linked, it only lasts in its container 24 hours. The optimal experiments or test are obtained after between 24 and 48 hours after application.

7. Safety:

When handling this product the instructions set out in the safety data leaflet must be observed. The relevant safety and precautionary measures for hygiene in the workplace must also be followed when working with chemical products.

8. Observations:

The instructions given in this publication are based on the current stand of our knowledge and experience. This does not presuppose any judicial guarantee concerning certain properties nor their suitability for any application in particular. Given the many influences that may occur during the handling and use of our products, the persons handling or transforming them are not exempt from carrying out their own controls or tests. All those receiving our products will be responsible for observing all existing patent rights as well as all current laws and regulations.

Update: 02.10.17

Finishing

Urethane
Resins