

# Qinoil 252

## 1. Introduction:

Sulfited oils, natural of marine and synthetic origin.

## 2. Description:

Oxidized sulphited oil.

## 3. Composition:

Appearance:	Liquid.
Character:	Anionic.
Active substance:	52±1%
pH value (1:10):	7.0±1
Color:	Brown

## 4. Properties:

For all types of leather that must be soft. Qinoil 252 also provides a round and filled feel. Given its composition, this fatliquor can be used as a single fatliquor. It can be applied during the rechroming, neutralization and greasing processes.

## 5. Minimum storage capability:

The product may be stored with its container tightly closed in a well-ventilated place at a temperature ranging from +5°C to +35°C. Sealed containers have a service life of 6 months.

## 6. Application:

The amounts to apply will depend both on the final softness of the leather to be treated and on the place where the fatliquor is placed. Normally in the rechroming of thick and firm leathers, between 0.5 and 1.0% is used and in a normal fatliquoring from 2% to 4%.

## 7. Safety:

When handling this product the instructions set out in the safety data leaflet must be observed. The relevant safety and precautionary measures for hygiene in the workplace must also be followed when working with chemical products.

## 8. Observations:

The instructions given in this publication are based on the current stand of our knowledge and experience. This does not presuppose any judicial guarantee concerning certain properties nor their suitability for any application in particular. Given the many influences that may occur during the handling and use of our products, the persons handling or transforming them are not exempt from carrying out their own controls or tests. All those receiving our products will be responsible for observing all existing patent rights as well as all current laws and regulations.

Update: 25.01.23

Beamhouse  
and Wet

Fatliquoring

More info

[quimicainternacional.com](http://quimicainternacional.com)