

1. Introduction:

Aqueous solution of an anionic polymer.

2. Presentación:

Aqueous solution of an anionic polymer.

3. Composición:

Polymeric retanning agent: polymerization product of carboxylic acids and their derivatives, especially esters.

Appearance:	Liquid.
Color:	Yellowish.
Character:	Anionic.
Solid matter:	40%
pH (1:10):	7.0-8.0

4. Properties:

It improves the wet-end process, be it neutralizing, retanning and greasing, thanks to its dispersing power as well as for rewetting dry skin. Recommended for leather waterproofed with the WP-QIN range of waterproofing products. Recommended for use in car upholstery due to its high fastness and very low fogging. Free of organic halogens and does not contribute to AOX in wastewater. Contains no organic solvents, ethoxylated alkylphenols, or formaldehyde. Resistant to light and yellowing at high temperatures. Due to its high performance, it allows reducing the amounts of other products that work alongside it as it improves their performance. Water repellents are easier to apply. It also helps to improve the penetration of the dye through the entire thick of the skin.

5. Minimum storage capability:

The product may be stored with its container tightly closed in a well-ventilated place at a temperature ranging from +5°C to +35°C. Sealed containers have a service life of 6 months.

6. Application:

It can be applied in the neutralization, using from 2% to 4% depending on the type of article. If it is put on after neutralization, it is recommended that it to be in a new bath. The improvement of the distribution in the retanning process can be achieved by adding 0.5% to 1% which, at the same time, will help the penetration of the dye. If it is a question of stabilizing normal greases or for waterproofing, it is advisable to add 10% of the overall greasing package. If you are trying to rewet dry leather, it is recommended between 2% and 4% on the weight of dry leather.

7. Safety:

When handling this product the instructions set out in the safety data leaflet must be observed. The relevant safety and precautionary measures for hygiene in the workplace must also be followed when working with chemical products.

8. Observations:

The instructions given in this publication are based on the current stand of our knowledge and experience. This does not presuppose any judicial guarantee concerning certain properties nor their suitability for any application in particular. Given the many influences that may occur during the handling and use of our products, the persons handling or transforming them are not exempt from carrying out their own controls or tests. All those receiving our products will be responsible for observing all existing patent rights as well as all current laws and regulations.

Update: 14.10.21

Products for
waterproofing

Auxiliary
wet end
products for
the waterproof
process