

## 1. Introduction:

Product for leather tanning.

## 2. Presentation:

Retanning agent for all kinds of hides.

## 3. Composition:

Condensation product based on sulphone and aromatic sulphonic acids.

Appearance:	Pulverish solid.
Nature:	Anionic.
Solids content:	approx > 80 %.
pH value (1:10):	8,5±1
Colour:	Beige.

## 4. Properties:

It features a good buffing capability, with good heat and light fastnesses. Good filling capability, especially over the parts where grain looseness can become deeper. It provides the leather with a soft and round touch feel, as well as with a fine pore. We will get shiny and even dyeings. It does not harm the presence of formaldehyde over the hide.

## 5. Minimum storage capability:

The product can be stored well closed in its own container, at a well ventilated place and at temperatures between + 5°C and +35°C. Inside its sealed container, it lasts for 12 months.

## 6. Application:

Purposed for all kinds of hides. Added either along with the main retanning agents pack or after stuffing, it provides the above mentioned. Quantities to be added vary between 3% and 8 %.

## 7. Safety:

When handling this product the instructions set out in the safety data leaflet must be observed. The relevant safety and precautionary measures for hygiene in the workplace must also be followed when working with chemical products.

## 8. Observations:

The instructions given in this publication are based on the current stand of our knowledge and experience. This does not presuppose any judicial guarantee concerning certain properties nor their suitability for any application in particular. Given the many influences that may occur during the handling and use of our products, the persons handling or transforming them are not exempt from carrying out their own controls or tests. All those receiving our products will be responsible for observing all existing patent rights as well as all current laws and regulations.

Update: 04.07.16

Beamhouse  
and Wet

Synthetic  
retanning agents