

Tanqin SS

1. Introduction:

Product for leather retanning.

2. Presentation:

Retanning agent.

3. Composition:

Condensation of a phenol sulphonic acid.

Appearance:	powder.
Nature:	anionic.
Solids content:	93%±1
PH Value (1:10):	4,0±0,5
Colour:	white.

4. Properties:

Tanqin SS gives a considerable filling to the leather, as well as sufficient softness. It allows to produce milled items and a very uniform and strong grain. The leathers retanned with this product show a good attitude for buffing. With its self-tanning properties, it also can be used to produce wet-white or chrome-free items.

5. Minimum storage capacity:

The product can be stored in its well closed container in a well ventilated place at temperatures between +5° and +35°C. In its sealed container it lasts 12 months.

6. Application:

In addition to its application for retanning, it can also be used after the fatliquoring and before its fixation (from 2 to 4%), giving big softness and good properties for milling and filling. In case of helping the grain solidity, it can be used to complete the rechroming with a certain quantity of this product (1 to 2%).

7. Safety:

When handling this product the instructions set out in the safety data leaflet must be observed. The relevant safety and precautionary measures for hygiene in the workplace must also be followed when working with chemical products.

8. Observations:

The instructions given in this publication are based on the current stand of our knowledge and experience. This does not presuppose any judicial guarantee concerning certain properties nor their suitability for any application in particular. Given the many influences that may occur during the handling and use of our products, the persons handling or transforming them are not exempt from carrying out their own controls or tests. All those receiving our products will be responsible for observing all existing patent rights as well as all current laws and regulations.

Update: 12.09.14

Beamhouse
and Wet

Synthetic
retanning agents